

ShaliGrout IP

Single Component Injection / Pressure Grout For Cement / Mortar / Concrete



Description

ShaliGrout IP is a plasticized and non-shrink cement / mortar admixture for pressure / injection grouting. By introducing into the cementitious grout, it reduces water cement ratio and facilitates volume expansion without segregation or bleeding. It may also be used to get water tight dense structures. It complies with BS 8110 part 1, 1985, section 8.9.4.6.

Characteristics

Compressive Strength 50 mm cube, kg/Cm ²	Increases due to reduced water cement ratio	Setting time	Does not effect
		Chloride Content	NIL
Expansion	1 to 4% unrestrained expansion to compensate for plastic shrinkage of cement. Time for expansion will be 15 minutes to 2 hours depending on temperature		

Application

- Bed grouting
- Pre-stressed cable duct grouting
- Non shrink infilling & joints at RCC hume pipes
- Tunnel linings
- Water Tank pressure grouting
- Flat as well as slopping roof
- Stationery machine foundation grouting

Advantages

- Gaseous expansion to compensate plastic shrinkage of cement
- Reduced w/c ratio to ensure low permeability and increased cohesion
- Hydrophobic additives give better water tight structure
- Free of chloride
- Does not attack reinforcement or prestress cables

Application Methodology

- Add ShaliGrout IP @ 1 % by weight of cement for neat cement on 2 % by weight of cement in case of concrete / mortar.
- For some special case, a higher dosage may be used in consultation with STP's technical team.
- Over-dosing increases expansion and causes frothing.
- **ShaliGrout IP** is compatible with all kinds of Portland cement, including SRC (Sulphate Resistant Cement), but is incompatible with high alumina cement. It is strongly recommended not to use **ShaliGrout IP** with cement having high alumina content.

Health & Safety

- Use mask, nose cover and hand gloves during application.
- Clean hands with soap water after application.

- Avoid contact with skin / eyes. In case of unlikely contact with eyes, rinse immediately with plenty of clean water, then cleanse with soap and lukewarm water and seek medical advice. Do not use solvent to clean the contacted area.
- Prevent swallowing. In case of unlikely swallowing, seek medical attention immediately. Do not induce vomiting.

Packing

Available in carton containing 1 kg x 12 Nos.or in 20 kg bag.

Storage

Store in cool dry place, under the shed, away from heat.

Shelf Life

9 months in original unopened sealed conditions.



STP Limited
Advisory Cell
+91 81302 81114
Waterproofers to the Nation

STP's Businesses
Waterproofing & Insulation
Road Surfacing
Pipeline Coating
Repairs & Rehabilitation
GARA (Grouts & Admixtures)
Other Powder Products
Sealant & Additives
Epoxy Flooring
Protective / Anti-Corrosive Coating
Other Products



Call us : +91 81302 27368
Nilkamal Paints & Hardware