ShaliPlast SP PQC



Chloride Free Superplasticiser for Pavement Quality Concrete

Description

ShaliPlast SP PQC is based on Sulphonated Napthalene Polymers and is supplied as a brown liquid instantly dispersible in water. ShaliPlast SP PQC has been specially formulated to give high water reductions upto 25% without loss of workability or to produce high quality concrete of reduced permeability. ShaliPlast SP PQC is specially formulated to meet the requirements of PQC. It conforms to IS:9103:1979 and BS:5075 Part 3 and ASTM-C-494 Type 'G' as a high range water reducing admixture.

Characteristics

conforms to IS:9103:1979 and reducing admixture.	BS:5075 Part 3	and ASTM-C-494 Type 'G'	as a high range water
Characteristics			9 6
pH @ 27 °C	7.0 - 8.0	Specific gravity @ 27 °C	1.200 ± 0.04
Chloride content, %	< 0.05	Air entrainment, %	< 1.5
Application High performance concrecte. Ready mix concrete. Flowing concrete. Heavily reinforced concrecte. Pumpable concrete. Concrete for precast slate.	ete.	250 21	Acto
Advantages	0		
 Improved workability. Increased strength. Improved quality. Higher cohesion. Chloride free. 	*9	oiln	

Application

- High performance concrete.
- Ready mix concrete.
- Flowing concrete.
- Heavily reinforced concrete.
- Pumpable concrete.
- Concrete for precast slabs

Advantages

- Improved workability.
- Increased strength.
- Improved quality.
- Higher cohesion.
- Chloride free.

Application Methodology

- Add ShaliPlast SP PQC to the dosing water. It should not come in contact with dry cement.
- Charge all concrete material in the proper order into the mixer with about 70 % of the mixing water and mix for appropriate time. Add rest quantity of water with admixture to obtain the required slump and mix for additional 2 – 3 minutes.
- Narrow sections must be watertight, strong and must have good bracing.
- During the "Flowing period" the concrete will exert a higher pressure at the base of the form than conventional concrete.
- Compatible with all types of Portland cement including SRC (Sulphate Resistance Cement) and not compatible with high alumina cement.

Dosage

The optimum dosage is best determined by site trials with the concrete mix which enables the effects of workability, strength gain or cement reduction to be measured. Site trials with ShaliPlast SP PQC should always be compared with mix containing no admixture. As a guide, the rate of addition is generally in the range of 0.6 - 1.5 % by weight of cement. Over dosage may cause Increase in air entrainment, Increase in workability, Retardation of initial and final setting times.

Health & Safety

- ShaliPlast SP PQC is non-toxic.
- Any splashes on the skin should be washed immediately with water.

• Splashes on the eyes should be washed immediately with water and seek medical advice.

Packing

Available in 250 kg drum.

Storage

Store in a cool dry place, under shed, away from heat.

Shelf Life

12 months in original sealed condition.



STP's Businesses
Waterproofing & Insulation
Road Surfacing
Pipeline Coating
Repairs & Rehabilitation
GARA (Grouts & Admixtures)
Other Powder Products
Sealant & Additives
Epoxy Flooring

Epoxy Flooring
Protective / Anti-Corrosive Coating
Other Products



