TarFelt FG – Grade 1 & 2

Glass Fiber Based Bituminous Waterproofing Membrane



Description

TarFelt[®] **FG** is Glass Fiber based Bituminous Waterproofing Felt produced by coating a centre core of 40 gsm Glass Fiber with bituminous coatant on both sides. Mica / sand is then spread over top and bottom layer to prevent inter layer sticking. It conforms to S: 7193 / 2013.

TarFelt FG is supplied in two variants – Grade 1 & Grade 2, which are respectively in conformity with IS:1346:1991 (suitable for application on surfaces such concrete, corrugated asbestos / GI sheet, timber, shell / folded plate etc) and IS:1609:1991 (suitable for silos, grain godowns, warehouses, wagons, trams, buses etc). **TarFelt FG - Grade 2** is mainly used for damp proofing treatment for foundation, basements and retaining walls

Characteristics

| Breaking Strength, | | Heat Resistance at 68 ± 2 °C, 3 hr | No flow |
|------------------------------|-------------|--------------------------------------|-------------|
| kg, Min | | Pressure Head Test at 300 mm | No Leakage |
| Wrap way | 50 | height of water | |
| Weft way | 30 | Storage sticking at 55 ± 2 °C, 18 hr | No Sticking |
| Pliability at 23 ± 1 °C | No crack on | Water absorption, %, Maximum | 2 |
| | unrolling | | |

Application

As given under Description above.

Advantages

- Resistant to chemicals of corrosive nature.
- Rot proof.
- Proven waterproofing first generation membrane and offers impermeability to water.
- Dimensionally stable.
- Ideal waterproofing material where atmosphere is corrosive or prone to chemical vapour.
- Effective for use on walls of effluent treatment plants.

Application Methodology

- Specification regarding the nature of treatment should be decided depending on the type of structure and climatic conditions. For example, in severe climatic conditions a heavy / extra heavy treatment should be adopted.
- Provide adequate number of drainage outlets of 100 mm diameter at least for every 40 m² of roof area.
- Clean the surface thoroughly to make it free from any foreign material. Repair all undulation and surface defect like cracks, honeycombing etc.
- PCC / cementitious coving of 75 mm radius shall be provided at all junction between vertical and horizontal faces.
- Apply a coat of ShaliTex Primer minimum @ 0.25 L / m² and allow it to dry completely.
- Use STP Bitumen 85/25 as bonding material which is to be prepared by heating it to the correct working temperature and spreading over the roof properly and uniformly @ 1.2 kg / m² per coat for waterproofing application or as specified.
- Unroll and fix TarFelt® FG by applying uniform pressure with hand for removal of any entrapped air.
- Provide overlap joints of 75 mm in longitudinal direction and 100 mm in transverse direction of the TarFelt® FG roll and seal it properly with hot bitumen.

- Terminate TarFelt® FG at the top of parapet if the height of parapet is up to 450 mm. In case the height of the parapet is above 450 mm, terminate TarFelt® FG at parapet in a groove 75 mm x 65 mm at a height of 150 300 mm from the finished roof level and groove shall be filled up with cement-sand mortar (1:4) with addition of ShaliPlast LW @ 200 ml / bag of cement.
- Top coat shall be finished with a layer of stone grit or pea gravel (6 mm and down size) which shall be laid by spreading it over a hot bitumen coat @ 1.2 Kg / m² laid over the felt.
- In case of non-trafficable roof, over the finished coat of bitumen, apply a coat of SuperSilverShield, bituminous based aluminium paint, @ 0.125 L / m².
- For a trafficable roof, protect membrane with PCC / Tiles. In case of PCC, ShaliPolyFibre @ 600 grm/m³ and ShaliPlast LW+ / STP No 1 (Liquid) @ 200 ml / bag of cement to be added to improve the resistance to crack formation and as well as waterproofing properties of screed.
- Use ShaliBond BS/CS cold adhesive wherever hot application is difficult or not permitted.
- For multi-layer treatment, stagger all the joints.

Health & Safety

- Use goggles, hand gloves and shoes during application.
- Clean hands with a mild solvent and thereafter wash with warm soap water.

Packing

- Grade 1 1 m x 20 m roll weighing 36 Kgs
- Grade 2 1 m x 10 m roll weighing 25 Kgs

Storage

Keep in a cool dry place, under shed, away from heat. Do not stack more than three rolls in one column.



STP's Businesses
Waterproofing & Insulation
Road Surfacing
Pipeline Coating
Repairs & Rehabilitation
GARA (Grouts & Admixtures)
Other Powder Products
Sealant & Additives
Epoxy Flooring
Protective / Anti-Corrosive Coating

Other Products



