

• Surface infected with algae/fungi needs to be removed thoroughly by vigorous wire brushing and water jetting or should be treated by 3% solution of bleaching powder & potable water. Allow it to react for 6-8 hours.

PUTTY (If required)

• Apply a thin coat of Shalimar Shakti Wall Guard Putty to fill any dents/minor hair line cracks or to smoothen the surface. Allow it to dry for 6-8 hours.

PRIMING

- Apply a coat of Shalimar (Exterior Primer/ Shakti Acrylic Primer) by thinning with potable water 40-50% by volume.
- Allow it to dry for 4-6 hours.

TOP COAT

- Apply 2-3 coats of Shalimar Xtra by thinning with potable water 40% by volume.
- Maintain a gap of 4-6 hours between coats.
- Avoid excess dilution for better performance.

Application Surfaces: All kinds of exterior plasters, concrete and masonry surfaces.

Apply an additional coat of Shalimar Xtra on horizontal surfaces or parapets for extra protection.



Finish	Smooth with Matt
Coverage	110 – 130 sq. ft. per litre per coat. (depends on substrate and application conditons)
Supply Viscosity	11+/- 3 poise at 30°C
Surface Dry	Within 25 minutes
Recoat Time	4 hours minimum
Thinner	Potable water
Primer	Apply a coat of Shalimar (Exterior Primer/ Shakti Acrylic Primer) by thinning with potable water 40-50% by volume.
Pack Size	1 litre / 4 litre / 10 litre / 20 litre
Area of Application	Exterior masonry, brick work, rendering & concrete

Actual technical details may vary due to factors such as method & condition of application & type of surface

