# **BRITISH INTERIOR EMULSION**



British Interior Emulsion is an economic plastic emulsion paint designed for application on interior walls. It is formulated from a time tested co-polymer emulsion binder. British Interior Emulsion offers excellent smoothness and elegance to your interior walls, giving it a rich look. It has good water and alkali resistance properties, which makes the paint longer lasting.

## TECHNICAL DATA

Areas of application : Interior plasters, asbestos sheets, brick work and concrete

Viscosity of supply : 100-116 Krebs units on stormer viscometer at 30°C

**Recommended thinner** : 50-75% By volume with water

Method of application : Brush/ Roller

Covering capacity : 270-300 sq. ft. / ltr / coat (spreading by brushing) : 140-160 Sq. feet / ltr / 2 coats

**Drying time** : Surface dry 20-30 minutes (@28-30°C & 60  $\pm$  5% R. $\boxplus$ 

Re-coating period : About 4-6 Hrs.
Finish : Smooth and Matt
Shades available : As per shade card
Packs available : 20 ltr, 10 ltr, 4 ltr & 1 ltr



### A) Surface preparation

Newly plastered surface must be allowed to mature for a minimum period of six months. The surface should be sanded to remove loose particles, paint, dust / grease, cracked or flaked paint. Previous coating of lime wash, powder distemper or other finish must be scrapped off. In case of repainting, earlier coating, need not be removed if in sound condition. The gloss / sheen of these coatings should be reduced to matt level by sanding. Surface imperfections / dents may be filled with suitable putty.

#### B) Application

Apply a coat of British Paints Primer (Water Thinnable or Solvent Thinnable) wherever necessary. Use about 50-70% of water for thinning. Add this water slowly to the paint and mix gently and homogeneously. For repainting jobs first coat can work as a self-priming coat. Apply two or three coats by brushing, keeping an interval of about four hours between successive coats. By tinting British Emulsion with Xtratone Universal Stainers, you can make shades of your own choice. The tinting process must be carried out before thinning.

(The information herein is given in good faith. Covering capacity is indicated on the basis of results obtained on a prepared smooth surface).



#### **Special Features**

Economy Emulsion | Smooth Finish | Available in White, Base White & 8 Tinting Bases





