

CONCRETE COATINGS

Anticarb Pro Clear

Scope

A single pack, solvent based, penetrating silane siloxane sealer coating designed for protection of concrete from carbonation distress. With suitable top coat it shall protect concrete surfaces of industrial installations exposed to severe and aggressive atmospheres.

Uses

Ideal for use as a sealer to protect exposed reinforced concrete structures of bridges, tunnels, exterior of water tanks, reservoirs, and other infrastructures situated in aggressive marine and coastal atmospheres

Product data

Туре	Single Pack	
Composition	Solvent based silane-siloxane	
Application	Brush, Roller, Spray	
Recommended DFT	The coating will fill porosity and seal the surface	
Volume Solid	10%	
Mixing of Thinner	not recommended	
Theoretical Spreading Rate	2.5m ² approximately and depends on surface porosity	
Drying Time	Surface dry: 1hr	
Overcoating Interval	minimum 24 hrs @30°C	
Colour	Colourless Clear	
Thinner/Cleaner	Thinner 828 (for cleaning of tools; not for mixing with product)	
Finish	Clear	
Packing	20Ltr	
Storage Life	Upto nine months as long as the sealed containers are kept in	
	a cool dry place (100 to 350C) and in original unopened	
	contaniers.	



BERGER W Protecton PROTECTIVE COATINGS

Anticarb Pro Clear

Substrate preparation

Concrete substrate must be fully cured, dry, sound and clean. It shall be free from other contaminants, such as curing compounds, sealers, oil, grease, dust, salts etc. The guideline standards for preparation of concrete is as per SSPC SP 13; Cleaning with required tools to free from contaminants, laitance, loosely adhering concrete, dust by mechanical, chemical and or thermal methods

Weak concrete must be removed. All voids, dents are to be repaired. All cracks, dents and voids depending on the size and depth should be filled suitably with putty or mortar after priming. Spot priming should be done after repair.

Application guidelines

Substrate temperature should be between 15°-35°C. Relative humidity during application should not be more than 80%. Substrate moisture content should be lower than 5%. The contents should be agitated with a slow speed stirrer to obtain a homogeneous mix. No thinning has to be done for application of primer. Application is suggested by hand brush to ensure better penetration into concrete. For highly absorbant surface a second coat of primer may be required; consult Berger technical team.

Precautions

Ensure substrate free of contaminants and solvents after surface preparation. As a general precaution forced ventillation should be provided when applying coating in confined spaces. Inhalation of solvent vapours, or coating mist and contact with skin or eyes should be avoided. Safety precautions as with any epoxy compounds should be adhered. Refer MSDS and health and safety guidelines.

Painting Systems

Product	Coat	Thickness
Anticarb Pro Clear	one	10- 15 microns
Anticarb Pro Coating	two	75 microns per coat

DISCLAIMER

The information contained within this Data Sheet is based on information believed to be reliable at the time of its preparation. The Company will not be liable for loss or damage howsoever caused including liability for negligence, which may be suffered by the user of the data contained herein. It is the users' responsibility to conduct all necessary tests to confirm the suitability of any product or system for their intended use. No guarantee of results is implied since conditions of use are beyond our control.

Data Sheet 203 Apr-09

BERGER PAINTS INDIA LIMITED

Berger House, 129 Park Street, Kolkata - 700017

Phone : (033) 2229 9724 (5 lines)/2249 9754 (4 lines) Fax : 91-33-2249 9729 / 2249 9009 Email : NORTH : protectondelhi@sify.com SOUTH : bpil_ch2@sify.com

EAST: bpil_cl1@vsnl.net WEST: bpilmum_prot@mtnl.net.in