

ASIAN ALUMINIUM PAINT

Alkyd

PRODUCT DESCRIPTION

Two pack, air drying, synthetic resin based aluminium finish

FEATURES AND RECOMMENDED USE

- Excellent durability and corrosion resistance
- Good adhesion and flexibility
- Good weather resistance & water resistance
- Heat resistance up to 120°C

TECHNICAL DATA

Colour	Aluminium
Gloss	Bright Metallic
Volume Solids	Approx. 23%
Recommended DFT / Coat	10 - 15 microns
Theoretical Coverage Capacity	23.0 sq.mtr/ ltr @ 10 microns DFT 15.3 sq.mtr/ ltr @ 15 microns DFT
Drying time at 30°C	Surface Dry : 4 hours Hard Dry : 16 hours
Over coating interval at 30°C	Min. : 16 hours Max. : Unlimited, provided surface is dry and clean from all contamination.

The data given is for guideline only. The physical values are subject to normal manufacturing tolerances, colour and testing variances

The volume solids indicated are as per ASTM D 2697 air drying method.

The actual drying time/ overcoat interval may be shorter or longer, depending on film thickness, ventilation, humidity, temperature etc.

The information provided above is at 30°C and 65% relative humidity.

DIRECTIONS FOR USE

Surface Preparation

General

- Suitable conventional primer or epoxy primer, dry and free from any contamination
- Surfaces must be dry, clean and free from contaminants
- Ensure removal of dirt, dust, oil and all other contaminants that could interfere with adhesion of the coating
- Oil and grease should be removed as per SSPC-SP1 solvent cleaning
- Surface should be checked and treated in accordance with ISO 8504 prior to priming

Blast Cleaning

- Steel, blast clean to Sa 2.5 of Swedish specification
- A blasting profile of (Rz) 30 - 40 microns is recommended
- In case blast cleaning is not possible, surface should be cleaned to St 3 using power tools

Application Conditions

- Substrate temperature should be at least 3°C above dew point but not above 50°C.
- Relative humidity should be below 85%
- Good ventilation is required in confined areas to ensure proper curing

Mixing

- Mix the entire quantity of supplied aluminium paste thoroughly with a small quantity of medium and then add the mixture to the remaining medium. Stir well before use.

Mixing Ratio (by weight)	Medium : Aluminium Pest 88 : 12
Pot Life at 30°C	Not Applicable

Application

Air Spray	
Recommended thinner	T - 284
Volume of thinner	Nil
Nozzle orifice	1.5 - 3.0 mm
Nozzle Pressure	0.3 – 0.4 MPa (= approx. 3 – 4 atm; 43 – 57 p.s.i.)
Cleaning Thinner	T - 284
Brush / Roller	
Recommended thinner	T - 284
Volume of thinner	Nil

Note:

- For best results, use the mixed paint within 6 hours of mixing.
- The larger period will reduce the lustre of the paint.
- Product should not be applied on hot surfaces

Cleaning

- Do not allow the product to remain in hoses, gun or spray equipment. Clean all equipments immediately after use with thinner T -284. It is recommended to periodically flush out spray equipment during the course of the working day. The frequency of cleaning will depend on amount sprayed, temperature and time gap.
- All surplus material and empty containers should be disposed off in accordance with appropriate regional legislation.

Product Characteristics

- The maximum performance is achieved after complete drying.
- At higher relative humidity, drying may get retarded
- Application of suitable primer will improve corrosion resistance
- Not recommended for use in highly acidic environment or where acid/ alkali spillage occurs

PACK SIZE	20 ltrs
STORAGE	Shelf Life: Atleast 12 months @ 30°C for original unopened pack, subject to inspection thereafter. Store in a cool, dry place and in accordance with local regulations
REGULATORY INFORMATION	Flash point: Not less than 30°C VOC: 610 ± 10 gm/ ltr (depending on shades)as per USA-EPA Method 24 Product Weight: Approx 0.88 ± 0.02 kg/ ltr

SAFETY INFORMATION

- As a general safety measure, inhalation of solvent vapours or paint mist and contact of liquid paint with skin & eyes, should be avoided. Forced ventilation should be provided when applying paint in confined spaces or stagnant air. Even when ventilation is provided, respiratory, skin and eye protection are always recommended when spraying paint.
- Please refer our Material Safety Data Sheet prior to using the product.



Call us : +91 98250 27368
Nilkamal Paints & Hardware

Disclaimer: To the best of our knowledge the information provided herein are true and accurate at the date of issuance. Since we have no control over the quality or condition of the substrate or the various factors affecting the use and application of the product, we do not accept any responsibility or liability arising out of use of the product. The company reserves the right to modify data contained herein without prior notice. Any change in data would normally be followed by issue of a new data-sheet. The user should check with the nearest sales office of the company and confirm the validity of the information, prior to using the product.

'ASIAN' is Trademark of Asian Paints Ltd | Licensed user: Asian Paints PPG Pvt. Limited.

Head Office: Asian Paints PPG Private Limited, Plot No-5, Gaiwadi Industrial Estate, Near Religare Building, S.V. Road, Goregaon (W), Mumbai 400 062. **Tel No:** 022 61089800, **Email:** customercare.apppg@asianpaintsppg.com, **Website:** www.asianpaintsppg.com