

## ASIAN CR ENAMEL



## PRODUCT DESCRIPTION

Single pack, air drying, high gloss finish paint

## FEATURES AND RECOMMENDED USE

- Suitable for industrial atmospheric conditions
- Easy application by brush with good flow
- Suitable for exterior and interior use

## TECHNICAL DATA

Colour	Range
Gloss	Glossy
Volume Solids	Approx. 34%
Recommended DFT / Coat	20 - 25 microns
Theoretical Coverage Capacity	17.0 sq.mtr/ ltr @ 20 microns DFT 13.6 sq.mtr/ ltr @ 25 microns DFT
Drying time at 30°C	Surface Dry : 4 hours Hard Dry : 12 hours
Over coating interval at 30°C	Min. : 12 hours Max. : Unlimited, provided surface is dry and clean from all contamination.

The data given is for guideline only. The physical values are subject to normal manufacturing tolerances, colour and testing variances

The volume solids indicated are as per ASTM D 2697 air drying method.

The actual drying time/ overcoat interval may be shorter or longer, depending on film thickness, ventilation, humidity, temperature etc.

The information provided above is at 30°C and 65% relative humidity.

## DIRECTIONS FOR USE

## Surface Preparation

## General

- Suitable primer or intermediate coat, dry and free from any contamination.
- Ensure removal of dirt, dust, oil and all other contaminants that could interfere with adhesion of the coating. Oil and grease should be removed as per SSPC-SP1 solvent cleaning.
- In case of aged coating, the surface should be sufficiently roughened if necessary

## Application Conditions

- Substrate temperature should be at least 3°C above dew point but not above 50°C.
- Relative humidity should be below 85%
- Good ventilation is required in confined areas to ensure proper curing

## Mixing

- If settling is observed in the drum, loosen the settled material with the help of hand stirrer followed by power driven stirrer for quick homogenous mixing
- Thinner should be added after mixing. Addition of excessive thinner will lead to reduced sag resistance.

## Application

<b>Air Spray</b>	
Volume of thinner	10 - 15%
Nozzle orifice	1.5 - 3.0 mm
Nozzle Pressure	0.3 – 0.4 MPa (= approx. 3 – 4 atm; 43 – 57 p.s.i.)
<b>Airless Spray</b>	
Volume of thinner	0 - 5%
Nozzle orifice	0.28 mm (11 Thou)
Nozzle Pressure	12 MPa (= approx. 120 atm; 1700 p.s.i.)
<b>Brush / Roller</b>	
Volume of thinner	0 - 5%

## Cleaning

- Do not allow the product to remain in hoses, gun or spray equipment. Clean all equipments immediately after use with suitable thinner. It is recommended to periodically flush out spray equipment during the course of the working day. The frequency of cleaning will depend on amount sprayed, temperature and time gap.
- All surplus material and empty containers should be disposed off in accordance with appropriate regional legislation.

## Product Characteristics

- The product is not recommended for continuous immersion in water or continuous splash of water
- The maximum performance is achieved after complete drying
- At higher relative humidity, drying may get retarded
- At higher DFT wrinkling of the surface will be seen

<b>PACK SIZE</b>	20 ltrs
<b>STORAGE</b>	<b>Shelf Life:</b> Atleast 12 months @ 30°C for original unopened pack, subject to inspection thereafter. Store in a cool, dry place and in accordance with local regulations
<b>REGULATORY INFORMATION</b>	<b>Flash point:</b> Not less than 35°C <b>VOC:</b> 550 ± 50 gm/ ltr (depending on shades) as per USA-EPA Method 24 <b>Product Weight:</b> Approx. 0.95 ± 0.06 kg/ ltr (depending on shades)

## SAFETY INFORMATION

- As a general safety measure, inhalation of solvent vapours or paint mist and contact of liquid paint with skin & eyes, should be avoided. Forced ventilation should be provided when applying paint in confined spaces or stagnant air. Even when ventilation is provided, respiratory, skin and eye protection are always recommended when spraying paint.
- Please refer our Material Safety Data Sheet prior to using the product.



Call us : +91 98250 27366  
Nilkamal Paints & Hardware

**Disclaimer:** To the best of our knowledge the information provided herein are true and accurate at the date of issuance. Since we have no control over the quality or condition of the substrate or the various factors affecting the use and application of the product, we do not accept any responsibility or liability arising out of use of the product. The company reserves the right to modify data contained herein without prior notice. Any change in data would normally be followed by issue of a new data-sheet. The user should check with the nearest sales office of the company and confirm the validity of the information, prior to using the product.

'ASIAN' is Trademark of Asian Paints Ltd | Licensed user: Asian Paints PPG Pvt. Limited.

**Head Office:** Asian Paints PPG Private Limited, Plot No-5, Gaiwadi Industrial Estate, Near Religare Building, S.V. Road, Goregaon (W), Mumbai 400 062. **Tel No:** 022 61089800, **Email:** customercare.apppg@asianpaintsppg.com, **Website:** www.asianpaintsppg.com