

APCOSIL 605 - ZS

Inorganic zinc rich silicate



PRODUCT DESCRIPTION

Two component, solvent based, moisture cured inorganic zinc silicate coating

FEATURES AND RECOMMENDED USE

- Heavy duty primer, offering excellent corrosion protection in highly aggressive environments for steel structures
- Excellent resistance to saline and marine / offshore atmosphere
- Recommended system primers in various high performance systems based on unsaponifiable binders
- Excellent water and solvent resistance
- Can withstand substrate temperatures from -90°C to +400°C, under normal atmospheric exposure conditions
- With suitable top coat, provides excellent corrosion protection for steel substrate upto +600°C

TECHNICAL DATA

Colour	Light Grey (self-standard)
Gloss	Matt
Recommended DFT / Coat	75 microns
Theoretical Coverage Capacity	7.5 – 8.0 Sq.mtr/ ltr
Drying time at 30°C	Surface Dry : 30 minutes Hard Dry : 8 hours Full Cure : 7 days
Over coating interval with recommended topcoats	Min. : 8 hours Max. : Unlimited, provided surface is free from any contamination, corrosion and zinc salt.
Method of Application	Air spray & Airless spray

The data given is for guideline only. The physical values are subject to normal manufacturing tolerances, colour and testing variances. The actual drying time/ overcoat interval may be shorter or longer, depending on film thickness, ventilation, humidity, temperature etc. The information provided above is at 30° C and 65% relative humidity.

DIRECTIONS FOR USE

Surface Preparation

General:

- Surfaces must be dry, clean and free from all contaminants
- Ensure removal of dirt, dust, oil and all other contaminants that could interfere with adhesion of the coating. Oil and grease should be removed as per SSPC-SP1 solvent cleaning.
- Surface should be checked and treated in accordance with ISO 8504 prior to priming

Blast Cleaning:

- Steel, abrasive blast clean to min. Sa 2 1/2 (ISO 8501-1: 200) or SSPC –SP6. In case oxidation has occurred between blasting and application of Apcosil 605-ZS the surface should be reblasted. A blasting profile of (Rz) 40-70 microns is recommended.
- Galvanised steel; sweep blast to roughen the surface and to remove any zinc salts that may be present.
- Heavily pitted steel is not acceptable

Application Conditions

- Substrate temperature should be at least 3°C above dew point but not above 50°C.
- Relative humidity should be above 50%
- Good ventilation is required in confined areas to ensure proper curing

Mixing

- Aposil 605-ZS is supplied in 2 packs, liquid component (hydrolysate) and a powder component (zinc dust).
- Do not open packing until just before use. Loosen the settled material in the liquid portion, if any, with the help of hand stirrer followed by power stirrer for quick homogeneous mixing.
- Add zinc dust gradually to the hydrolysate under stirring. Continue stirring until mixture is homogeneous. (Do not mix in reverse order. It may result in lump formation in the paint.) Strain mixture through a 30-60 mesh screen. Maintain constant agitation of the mixture until the batch is depleted. Once the unit has been mixed, it should be consumed within the working pot life.

Mixing Ratio (by weight)	Hydrolysate: Zinc dust (Liquid) : (Powder) 42 : 58
Induction Time	None
Pot Life at 30°C	4 hours

Application

Air Spray	
Recommended thinner	T 144
Volume of thinner	10 - 25 %
Nozzle orifice	2.0 - 3.0 mm
Nozzle pressure	0.3-0.4 MPa (= approx. 3-4 atm; 43-57 p.s.i)
Airless Spray	
Recommended thinner	T 144
Volume of thinner	10 - 25%
Nozzle orifice	0.48 - 0.64 mm
Nozzle pressure	15 MPa (= approx. 150 - 190 atm; 2100 p.s.i)
Brush / Roller	Not recommended

Cleaning

- Do not allow the product to remain in hoses, gun or spray equipment. Clean all equipments immediately after use with Thinner T 144.

Product Characteristics

- While application, the spray gun should be at a sufficient distance from the surface to get a wet and smooth coating. Besides using a correct spray technique, the amount of thinner added must be carefully adjusted to secure optimum film formation. The coating must be wet and smooth just after application.
- Inorganic Zinc Silicate Primers are sensitive to environmental conditions for drying and curing. This product requires minimum relative humidity of 50% and minimum steel temperature should be 10°C. In case skin temperature of steel is more than 40°C spraying shall be done by extra thinning to avoid dry spray application. At Relative humidity below 50%, curing will be severely retarded. The curing at low humidity may be promoted by spraying fresh water after 4-6 hours of application of primer and keeping the surface constantly wet until curing is complete.
- The product can be applied at a range of 50 – 75 microns/coat, however high deposition of film thickness (>125 microns) can result into mud-cracking while lower dry film thickness can affect the performance of coating. In case of mud cracking, complete removal of the affected areas by abrasive blasting and re-application as per original specification is recommended.
- Untopcoated Apcosil 605-ZS is not suitable for immersion in alkaline (more than pH 9) or acidic (less than pH 5) liquids without suitable topcoats.

Overcoating and Topcoats

- Before overcoating with recommended topcoats, ensure Apcosil 605-ZS is completely cured. The complete curing can be checked as per ASTM 4752 i.e 50 double rub of the coating with a cotton cloth soaked in thinner T 144 or MEK. If the coating remains unaffected, the curing is complete.
- Prior to overcoating, Apcosil 605-ZS must be clean, dry and free from soluble salts and zinc corrosion products. Zinc rich primers, when exposed for extended periods of time without proper top coating, will start showing white rust formation. These “white rust” spots are zinc corrosion products. The extent of white rust formation will depend on the period of exposure of the zinc rich coating and the nature of the surrounding environment. Prior to application of the subsequent coats, it is necessary to ensure removal of the white rust.
- Zinc rich coatings are porous and hence pinholes may occur in the subsequent coat due to solvent popping. To minimize pinholes, apply a mist coat as the first pass of the subsequent coat, let the entrapped air escape and then apply full coat.
- Apcosil 605-ZS may be topcoated with epoxies, pure chlororubber, acrylics, polysiloxanes, heat resistant silicones and others as recommended by Asian Paints PPG representative.

PACK SIZE	25 ltrs Hydroxylate : 20.86 ltrs in HDPE container Zinc Dust : 4.14 ltrs in 10 ltr pack
STORAGE	Shelf Life: Atleast 6 months @ 30°C for original unopened pack, subject to inspection thereafter. Store in a cool, dry place and in accordance with local regulations
REGULATORY INFORMATION	Flash Point: Liquid - Not less than 15°C Powder - Above 65°C VOC: 590 g/ ltr as per USA-EPA Method 24 Product Weight: 2.00 kg/ lt

SAFETY INFORMATION

- As a general safety measure, inhalation of solvent vapours or paint mist and contact of liquid paint with skin & eyes should be avoided. Forced ventilation should be provided when applying paint in confined spaces or stagnant air. Even when ventilation is provided, respiratory, skin and eye protection is always recommended while spraying paint.
- Please refer our Material Safety Data Sheet prior to using the product.

Call us : +91 98250 27368
Nilkamal Paints & Hardware



Disclaimer: To the best of our knowledge the information provided herein is true and accurate at the date of issuance. Since we have no control over the quality or condition of the substrate or the various factors affecting the use and application of the product, we do not accept any responsibility or liability arising out of use of the product.

The company reserves the right to modify data contained herein without prior notice. Any change in data would normally be followed by issue of a new data-sheet. The user should check with the nearest sales office of the company and confirm the validity of the information, prior to using the product

'APCOSIL is a Trademark of Asian Paints Ltd. | Licensed user: Asian Paints PPG Pvt. Limited.

Head Office: Asian Paints PPG Private Limited, Plot No-5, Gaiwadi Industrial Estate, Near Religare Building, S.V. Road, Goregaon (W), Mumbai 400 062. **Tel No:** 022 61089800, **Email:** customercare.apppg@asianpaintsppg.com, **Website:** www.asianpaintsppg.com